

Nylon66 Resin

First Grade	Relative Viscosity	Meq/kg-NH ₂	Meq/kg-COOH	Black Specks %	Moisture for Dry Resin (Mg/kg)	Ash %
EPR24	2.45±0.03	38±3	80±3	≤0.017	≤1500	
EPR27	2.67±0.03	50±3	70±4	≤0.017	-	
EPR27N	2.57±0.03	-	-	≤0.017	≤1800	
EPR2701	2.63±0.03	-	-	≤0.017	≤1500	
EPR2703	2.70±0.03	-	-	≤0.017	-	
EPR32	3.20±0.07	36±3	56±3	≤0.017	≤700	
FYR25BCL	2.55±0.03	45±3	78±4	≤0.017	≤900	
FYR25T03	2.47±0.03	41±3	79±4	≤0.017	≤900	0.30±0.01
FYR25T03CL	2.55±0.03	45±3	78±4	≤0.017	≤900	0.30±0.01
FYR25B	2.47±0.03	41±3	79±4	≤0.017	≤900	
FYR27	2.67±0.05	50±3	70±4	≤0.017	≤900	
FYR25HL	2.53±0.03	68±3	56±4	≤0.017	≤900	
FYR27B	2.67±0.05	50±3	70±4	≤0.017	≤900	
FYR27BH	2.67±0.05	88±4	33±3	≤0.017	≤900	
FYR27BC	2.63±0.05	38±5	85±5	≤0.017	≤900	